

Chemical resistance
Van de Lande B.V.
2012

+ Good resistance
~ Limited resistance
- Not resistant

Substance	Conc.	PVC-U		PVC-C		PP		PE		EPDM		NBR		FPM	
		20°C	60°C	20°C	80°C	20°C	60°C	20°C	60°C	20°C	60°C	20°C	60°C	20°C	60°C
Acetaldehyde	40%	~		-	-	+	+	+	~	+	+	-		+	~
	100%	-		-	-	~		+		+	-	-		~	
Acetic acid	<10%	+	+	+	+	+	+	+	+	+	~	+		+	~
	10-20%	+	+	~		+	+	+	+	+	~	+		+	~
	20-30%	+	+	~		+	+	+	+	~	~	-		+	~
	30-60%	+	+	~		+	+	+	+	~	~	-		~	~
>60%	+	-	~		+	+	+	~	~	~	-		-	-	
Acetic anhydride		-	-	-	-	+		+	~	~				-	-
Acetone	<5%	-	-	+	+	+	+	+	+	+	+	-	-	-	-
	>5%	-	-	-	-	+	+	+	+	+	+	-	-	-	-
Acrylic ester		-		-	-	-				~		-		-	
Acrylonitrile		-		-	-	+		+	+	+	~	-		~	-
Adipic acid		+	-	+	+	+	+	+	+	+	+	+	+	+	+
Alcoholic spirits	40%	+				+		+		+		+		+	
Allyl alcohol	96%	~	-	~		+	+	+	+	~	~	+	+	~	-
Aluminium chloride		+	+	+	+	+	+	+	+	+	+	+	+	+	+
Aluminium potassium sulphate		+	~	+	+	+	+	+	+	+	+	+	~	+	+
Aluminium sulphate		+	+	+	+	+	+	+	+	+	+	+	+	+	+
Ammonia, dry gas		+	+	-	-	+		+	+	+	~			+	
Ammonia, liquid		~	-	-	-	+		+		+				-	
Ammonium acetate		+	~	+	+	+	+	+	+	+	+	+		+	+
Ammonium carbonate	50%	+	~	+	+	+	+	+	+	+	+	+	+	+	+
Ammonium chloride		+	~	+	+	+	+	+	+	+	+	+	+	+	+
Ammonium fluoride	20%	+	~	+	+	+	+	+	+					+	+
Ammonium hydroxide		+	~	-	-	+	+	+	+	+	+	+	~	-	
Ammonium nitrate		+	+	+	+	+	+	+	+	+	+	+	~	+	+
Ammonium phosphate		+	+	+		+	+	+	+	+	+	+	~	+	+
Ammonium sulphate		+	+	+	+	+	+	+	+	+	+	+	~	+	+
Ammonium sulphide		+	~	+	+	+	+	+	+	+	+	+	+	+	-
Amyl acetate		-	-	-	-	~	-	+	+	~		-		-	
Amyl alcohol		+	~	~		+	+	+	~	+	+	+	+	+	
Aniline		-		-	-	~		+	+	-		-		~	~
Aniline hydrochloride		+				+	~	+	+	+	+	~		~	~
Antimony trichloride	90%	+		+	+	+	+	+	+	+		-		+	
Aqua regia		+		+	-	-		-		-		-		~	

The data are provided as is and there is no warranty or representation, neither express nor implied, that they are free from errors. Van de Lande B.V. shall not be liable for any damages of any kind that may result from the use of this data. The information often is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance or reproducibility. Formulations presented may not have been tested for stability and should be used only as a suggested starting point. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user.

Chemical resistance
Van de Lande B.V.
2012

+ Good resistance
~ Limited resistance
- Not resistant

Substance	Conc.	PVC-U		PVC-C		PP		PE		EPDM		NBR		FPM	
		20°C	60°C	20°C	80°C	20°C	60°C	20°C	60°C	20°C	60°C	20°C	60°C	20°C	60°C
Arsenic acid	80%	+	~	+	-	+	+	+	+	+	+	+	+	+	+
Barium hydroxide		+	~	+	+	+	+	+	+	+	+	+	+	+	+
Barium salts		+	+	+	+	+	+	+	+	+	+	+	+	+	+
Beer		+	+	+	+	+	+	+	+	+	+	+	+	+	+
Benzaldehyde		-	-	-	-	+	+	+	+	+	+	~	~	+	+
Benzene		-	-	-	-	~	-	~	-	-	-	~	~	+	+
Benzine		+	+	+	+	~	-	+	~	-	-	+	+	+	+
Benzoic acid		~	-	+	-	+	+	+	+	-	-	-	-	+	+
Benzyl alcohol		~	-	-	-	+	~	+	+	-	-	-	-	+	+
Borax		+	~	+	+	+	+	+	+	+	+	+	+	+	+
Boric acid		+	~	+	+	+	+	+	+	+	+	+	+	+	+
Bromine gas		-	-	-	-	-	-	-	-	-	-	-	-	+	+
Bromine liquid		-	-	-	-	-	-	-	-	-	-	-	-	+	+
Bromine water, aqueous, sat'd		+	+	+	+	-	-	-	-	-	-	-	-	+	+
Butadiene		+	+	+	+	+	+	~	-	-	-	-	-	~	~
Butane		+	+	+	+	+	+	+	+	-	-	+	+	+	+
Butanediol	10%	+	+	+	+	+	+	+	+	+	+	+	+	+	+
Butanol		+	~	~	~	+	~	+	+	+	+	+	+	+	-
Butyl acetate		-	-	-	-	~	~	+	~	+	-	-	-	~	-
Butyl phenol		~	-	-	-	+	+	+	+	-	-	-	-	~	-
Butylene glycol		+	~	+	+	+	+	+	+	+	+	-	-	+	~
Butylene liquid		+	+	+	+	-	-	-	-	~	~	+	+	+	+
Butyric acid	1%	+	-	+	+	+	+	+	+	+	+	-	-	+	+
	20%	+	-	-	-	+	+	+	+	+	+	-	-	+	+
	98%	-	-	-	-	+	+	~	~	~	~	-	-	~	~
Calcium bisulphite		+	+	+	+	+	+	+	+	+	+	-	-	+	+
Calcium chloride		+	~	+	+	+	+	+	+	+	+	+	+	+	+
Calcium hydroxide		+	+	+	+	+	+	+	+	+	+	+	~	+	+
Calcium hypochlorite		+	+	+	+	+	+	+	+	+	+	+	+	+	-
Calcium nitrate		+	+	+	+	+	+	+	+	+	+	+	+	+	+
Carbon dioxide, moist		+	~	+	+	+	+	+	+	+	+	+	+	+	+
Carbon dioxide, anhydrous		+	+	+	+	+	+	+	+	+	+	+	+	+	+
Carbon disulphide		-	-	-	-	~	~	~	-	-	-	-	-	+	+
Carbon tetrachloride		-	-	-	-	-	-	~	-	-	-	-	-	+	+

The data are provided as is and there is no warranty or representation, neither express nor implied, that they are free from errors. Van de Lande B.V. shall not be liable for any damages of any kind that may result from the use of this data. The information often is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance or reproducibility. Formulations presented may not have been tested for stability and should be used only as a suggested starting point. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user.

Chemical resistance
Van de Lande B.V.
2012

+ Good resistance
~ Limited resistance
- Not resistant

Substance	Conc.	PVC-U		PVC-C		PP		PE		EPDM		NBR		FPM	
		20°C	60°C	20°C	80°C	20°C	60°C	20°C	60°C	20°C	60°C	20°C	60°C	20°C	60°C
Chloral hydrate		-				~	-	+	+	~		-		~	
Chlorethanol		-				+	+	+	+	~		+		-	
Chloric acid	10%	+	~	+	+	-		+	+	+	+	-		-	
	20%	+	~	+	+	-		~		+		-		-	
Chlorine, aqueous		~	-			-	-	+	~	-	-	-	-	-	-
Chlorine, dry gas		~	-	-	-	-	-	~	-	-	-	-	-	+	-
Chlorine water		~		+	+	~		-		~		-		~	
Chloroacetic acid		+	~			+	+	+	+	~		-		+	
Chlorobenzene		-		-	-	+		~	-	-		-		-	
Chloroform		-		-	-	~		~	-	-		-		~	
Chlorosulphonic acid	100%	~	-			-	-	-	-	-	-	-	-	-	-
Chrome alum		+	+			+	+	+	+	+	+	+	+	+	+
Chromic acid	<50%	+	~	+	+	~	-	~	-	~	~	-		+	+
Cider		+		+		+		+	+	+		+		+	
Citric acid	20%	+	~	+	+	+	+	+	+	+	+	+	~	+	+
Coal gas, benzene free		+				+		+		-		+		+	
Compressed air, containing oil						~		+		-		+		+	
Copper chloride		+	+	+	+	+	+	+	+	+	+	+	+	+	+
Copper fluoride	2%	+	+	+	+	+	+	+	+	+	+	+	~	+	+
Copper salts		+	~	+	+	+	-	+	+	+	+	+	~	+	+
Copper sulphate		+	+	+	+	+	+	+	+	+	+	+	~	+	+
Cresols		~	-	-	-	+	-	+	~	-	-	~		~	
Crotonic aldehyde		~		-	-	+		+		+		+		+	
Cyclohexane		-		-	-	+		+	+	-		+		+	
Cyclohexanol		+	+	-	-	+	~	+	+	-		~		+	
Cyclohexanone		-	-	-	-	+	~	+	~	~		-	-	-	-
Densodrine		+	+									+		+	
Detergents		+	~	~		+	+	+	+	+	+	+	+	+	+
Dextrine		+	+	+	+	+		+	+	+	+	+	+	+	+
Dichloroacetic acid		+	~			+	~	+	~	+	+	-		~	
Dichloroethane		-	-	-	-	~		~	~	~		-		-	
Dichloromethane		-	-			~	-	~	~	-	-	-		~	
Diesel oil		+				~		+	~	-		+		+	
Diethylamine	30%	~		-	-	+				~		-		~	

The data are provided as is and there is no warranty or representation, neither express nor implied, that they are free from errors. Van de Lande B.V. shall not be liable for any damages of any kind that may result from the use of this data. The information often is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance or reproducibility. Formulations presented may not have been tested for stability and should be used only as a suggested starting point. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user.

Chemical resistance
Van de Lande B.V.
2012

+ Good resistance
~ Limited resistance
- Not resistant

Substance	Conc.	PVC-U		PVC-C		PP		PE		EPDM		NBR		FPM	
		20°C	60°C	20°C	80°C	20°C	60°C	20°C	60°C	20°C	60°C	20°C	60°C	20°C	60°C
Diglycolic acid	30%	+	~			+	+	+	+	+	~			+	+
Dimethylamine		~				+		+	~	~		-		-	
Dioxane		-				~	~	+	+	+		~		-	
Ethanol	<5%	+	~	+	+	+	+	+	+	+	+	+	+	+	+
Ethyl acetate		-	-	-	-	+	~	+	~	~	~	-	-	-	-
Ethyl alcohol	96%	+	~			+	+	+	+	+	+	+	+	~	~
Ethyl chloride		-		-	-	~		~		-		-		~	
Ethyl ether		-		-	-	+		+	~	-		-		-	
Ethylene chloride		-		-	-	~		~		-	~	~		+	~
Ethylene diamine		~		-	-	+		+	+	+	+	~	-	~	-
Ethylene glycol	<50%	+	+	+	+	+	+	+	+	+	+	+	~	+	+
	>50%			~											
Fertilizer salts		+	~			+	+	+	+	+	+	+	+	+	+
Fluorosilicic acid	<25%	+	+	+	+	+		+	+	~	-	-	-	-	-
Formaldehyde	40%	+		-	-	+		+	+	+	+	+	~	+	+
Formamide		-				+	+	+	+	+		+		~	
Formic acid	<25%	+	~	+	+	+	~	+	+	+	~	-	-	+	~
	25-50%	+	~	~											
Fruit juices		+	+	+	+	+	+	+	+	+	+	+	+	+	+
Fuel oil		+				~		+	~	-		+	+	+	+
Furfuryl alcohol		-	-			+	~	+	+	~		-		~	-
Gelatine		+				+	+	+	+	+		+		+	
Glucose		+	~	+	+	+	+	+	+	+	+	+	+	+	+
Glycerine		+	+	+	+	+	+	+	+	+	+	+	+	~	+
Glycocoll	10%	+				+		+		+		+		+	
Glycolic acid	37%	+				+		+	+	+		+		+	
Heptane		+		~		+	~	+	~	-		+	+	+	+
Hexane		+				+	~	+	~	-		+	+	+	+
Hydrazine hydrate		+				+	+	+	+	+		-		+	
Hydrobromic acid	10%	+	+			+		+	+	+	+	-		+	+
	50%	+	~			+	+	+	+	+	~	~	-	+	+
Hydrochloric acid	<25%	+	+	+	+	+	+	+	+	+	+	-	-	+	+
	25-40%	+	~	+	+	+	~	+	+	~	~	-	-	+	~
Hydrocyanic acid		+	~			+	+	+	+	+		~		+	

The data are provided as is and there is no warranty or representation, neither express nor implied, that they are free from errors. Van de Lande B.V. shall not be liable for any damages of any kind that may result from the use of this data. The information often is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance or reproducibility. Formulations presented may not have been tested for stability and should be used only as a suggested starting point. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user.

Chemical resistance
Van de Lande B.V.
2012

+ Good resistance
~ Limited resistance
- Not resistant

Substance	Conc.	PVC-U		PVC-C		PP		PE		EPDM		NBR		FPM	
		20°C	60°C	20°C	80°C	20°C	60°C	20°C	60°C	20°C	60°C	20°C	60°C	20°C	60°C
Hydrofluoric acid	40%	~	-	-	-	+	~	+	~	-	-	-	-	+	
	60%	~	-	-	-	+	+	+	~	-	-	-	-	+	
	70%	~	-	-	-	+		+	~	-	-	-	-	+	
Hydrogen		+	~	+	+	+	+	+	+	+	+	+	+	+	+
Hydrogen chloride		+	~	+		+	+	+	+	+	+	~		+	+
Hydrogen peroxide	10%	+	~	+	+	+	+	~	-	+	-	~		+	-
	30%	+		+	+	+	~	~	-	~		-		+	~
	90%	+				-		~	~	~		-		~	
Hydrogen sulphide		+	+			+	+	+	~	+	-	+	-	+	~
Hydroxylamine sulphate		+				+	+	+	+	+		+		+	
Iron trichloride		+	~			+	+	+	+	+	+	+	+	+	+
Kerosene		+	+	-	-	+		+	~	~	-	+	~	+	+
Lactic acid	<10%	+	~	+	+	+	+	+	+	~	~	~	~	~	~
	10-25%	~	-	+	+	+	+	+	+	~	-			~	+
	>25%	~	-	+											
Lead acetate		+	+	+	+	+	+	+	+	+	+	+	+	+	+
Lead tetraethyl		+				+		+		~		+		+	
Magnesium chloride		+	~	+	+	+	+	+	+	+	+	+	+	+	+
Maleic acid	<50%	+	~	+	+	+	+	+	+	~	-	-		+	+
Methyl alcohol		+	~			+	+	+	+	+	+	+	+	~	~
Milk		+	+			+	+	+	+	+		+		+	
Mineral oil		+	+	+				+	~	-		+	+	+	+
Molasses		+	~	+		+	+	+	+	+	+	+	+	+	+
Nickel sulphate		+	+	+	+	+	+	+	+	+	+	+	+	+	+
Nitric acid	<50%	+	~	+	-	~	-	~	-	-	-			+	~
	>50%	-	-	+	-	-	-	-	-	-	-			-	-
Oils and Fats		+	+	-	-	+	+	+	~	-	-	+		+	+
Oleic acid		+	+			+	~	+	~	-		~	-	+	-
Oleum, 10% SO3		-	-	-	-	-	-	-	-	-	-	-	-	-	~
Oxalic acid		+	+	+	-	+	+	+	+	+	+	~	-	+	+
Oxygen		+	+	+	+	+	~	+	+	+	+	-		+	+
Ozone		+				~	-	~	-	+	-	-		+	-
Perchloric acid	10%	+	~	+		+	+	+	+	~	+	-	-	+	+
Perchloric acid	70%	-	-			~	-	+	-	+	~	-	-	+	~

The data are provided as is and there is no warranty or representation, neither express nor implied, that they are free from errors. Van de Lande B.V. shall not be liable for any damages of any kind that may result from the use of this data. The information often is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance or reproducibility. Formulations presented may not have been tested for stability and should be used only as a suggested starting point. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user.

Chemical resistance
Van de Lande B.V.
2012

+ Good resistance
~ Limited resistance
- Not resistant

Substance	Conc.	PVC-U		PVC-C		PP		PE		EPDM		NBR		FPM	
		20°C	60°C	20°C	80°C	20°C	60°C	20°C	60°C	20°C	60°C	20°C	60°C	20°C	60°C
Phenol	10%	+				+	+	+	~	+	+	-		+	+
Phenol	90%	~				+	+	+	~	-		-		+	-
Phenylhydrazine		-	-	-	-	~		~	-	~		-	-	+	~
Phenylhydrazine hydrochloride		~		-	-	+	~	+	-	+	~	~		+	~
Phosphine		+	+			+	+	+	+						
Phosphoric acid	<50%	+	+	+	+	+	+	+	+	+	+	~	-	+	+
	50-85%	+	+	+	+	+	+	+	~	+	+	-	-	+	+
Picric acid	1%	+		-	-	+		+		+	~	~		+	+
Potassium bichromate		+	~	+	+	+	+	+	+	+	+	+	+	+	+
Potassium borate	10%	+	~	+	+	+	+	+	+	+	+	+	+	+	+
Potassium bromate		+	~	+	+	+	+	+	+	+	+	+	+	+	+
Potassium bromide		+	+	+	+	+	+	+	+	+	+	+	+	+	+
Potassium chlorate		+	+	+	+	+	+	+	+	+	+	+	+	+	+
Potassium chloride		+	+	+	+	+	+	+	+	+	+	+	+	+	+
Potassium chromate		+	+	+	+	+	+	+	+	+	+	+	-	+	+
Potassium cyanide		+	+	+	+	+	+	+	+	+	+	+	+	+	-
Potassium dichromate		+	+	+	+	+	+	+	+	+	+	~		+	+
Potassium iodide		+	+	+	+	+	+	+	+	+	+	+	-	+	+
Potassium nitrate		+	+	+	+	+	+	+	+	+	+	+	+	+	+
Potassium perchlorate		+	~	+	+	+	+	+	~	+	+	+	+	+	+
Potassium permanganate		+	~	+	+	+	+	+	~	+	+	+	+	+	+
Potassium persulphate		+	~	+	+	+	+	+	+	+	+	-		+	+
Potassium phosphates		+	~	+	+	+	+	+	+	+	+	+	-	+	+
Potassium sulphate		+	~	+	+	+	+	+	+	+	+	+	+	+	+
Pyridine		-	-	-	-	~		+	~	+	~	-		~	
Sea water		+	~	+	+	+	+	+	+	+	+	+	+	+	+
Silver nitrate		+	~	+	+	+	+	+	+	+	+	+	+	+	+
Soap		+	~	+	+	+	+	+	+	+	+	+	+	+	+
Sodium acetate		+		+	+	+	+	+	+	+	+	+		+	+
Sodium benzoate		+	~	+	+	+	+	+	+	+	+	+		+	+
Sodium bicarbonate		+	+	+	+	+	+	+	+	+	+	+	+	+	+
Sodium bisulphate	10%	+	~	+	+	+	+	+	+	+	+	+	-	+	+
Sodium bisulphite		+	-	+	+	+	+	+	+	+	+	~	-	~	-
Sodium bromate		+				+		+		+	+	+	-	+	+

The data are provided as is and there is no warranty or representation, neither express nor implied, that they are free from errors. Van de Lande B.V. shall not be liable for any damages of any kind that may result from the use of this data. The information often is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance or reproducibility. Formulations presented may not have been tested for stability and should be used only as a suggested starting point. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user.

Chemical resistance
Van de Lande B.V.
2012

+ Good resistance
~ Limited resistance
- Not resistant

Substance	Conc.	PVC-U		PVC-C		PP		PE		EPDM		NBR		FPM	
		20°C	60°C	20°C	80°C	20°C	60°C	20°C	60°C	20°C	60°C	20°C	60°C	20°C	60°C
Sodium bromide		+	~	+	+	+	+	+	+	+	+	+		+	+
Sodium carbonate		+	+	+	+	+	+	+	+	+	+	+	+	+	+
Sodium chlorate		+	~	+	+	+	+	+	+	+	+	+	-	+	+
Sodium chloride		+	~	+	+	+	+	+	+	+	+	+	+	+	+
Sodium chlorite		~		+	+	+	~	+		+	+	-		+	+
Sodium chromate		+	~	+	+	+		+		+	+	+	-	+	+
Sodium disulphite		+	~			+		+		+	+	~		+	+
Sodium dithionite	10%	+	~			+	+	+	+	+	+	+	-	+	+
Sodium fluoride		+		+	+	+		+	+	+	+	+	~	+	+
Sodium hydroxide	10%	+	~			+	+	+	+	+	+	+	+	~	~
	50%	+	+			+	+	+	+	+	~	~	-	-	-
Sodium hypochlorite		+	~	+	+	~	-	~	-	+		-		+	
Sodium iodide		+	~	+		+		+		+	+	+	~	+	+
Sodium nitrate		+	~	+	+	+	+	+	+	+	+	+	+	+	+
Sodium nitrite		+		+	+	+		+	+	+	+	+	-	+	+
Sodium oxalate		+	~			+		+		+		+		+	
Sodium persulphate		+	~			+	+	+	+	+	+	-		+	+
Sodium phosphate		+	~	+	+	+	+	+	+	+	+	+	+	+	+
Sodium silicate		+	~	+	+	+	+	+	+	+	+	+	+	+	+
Sodium sulphate		+	~	+	+	+	+	+	+	+	~	+	+	+	+
Sodium sulphide		+	~	+	+	+	+	+	+	+	+	+	+	-	
Sodium sulphite		+	~	+	+	+	+	+	+	+	+	+	-	+	+
Sodium thiosulphate		+	~	+	+	+	+	+	+	+	+	+	-	+	+
Stannous chloride		+	+	+	+	+	+	+	+	+	-	+	~	+	+
Sugar		+	+	+	+	+	+	+	+	+	+	+	+	+	+
Sulfuric acid	<50%	+	~	+	+	+	+	+	+	+	+	~		+	+
	50-80%	+	-	+	+	+		+	~	+	-	-	-	+	+
	80-96%	~	-	+	-	-	-	~	-	-	-	-	-	+	-
Sulfurous acid		+	~	+	+	+	+	+	+	+	-	-	-	+	~
Sulphur dioxide, moist		~	-			+		+	+	+		-		+	
Sulphur dioxide, anhydrous		+	+			+		+	+	+		-		+	
Tannic acid	30%	+	+	+		+	+	+	+	+		+		+	+
Tartaric acid		+	+	+		+	+	+	+	+	-	+	~	+	+
Toluene		-	-	-	-	~	-	~	-	-	-	-	-	~	-

The data are provided as is and there is no warranty or representation, neither express nor implied, that they are free from errors. Van de Lande B.V. shall not be liable for any damages of any kind that may result from the use of this data. The information often is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance or reproducibility. Formulations presented may not have been tested for stability and should be used only as a suggested starting point. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user.

Chemical resistance
Van de Lande B.V.
2012

+ Good resistance
~ Limited resistance
- Not resistant

Substance	Conc.	PVC-U		PVC-C		PP		PE		EPDM		NBR		FPM	
		20°C	60°C	20°C	80°C	20°C	60°C	20°C	60°C	20°C	60°C	20°C	60°C	20°C	60°C
Trichloroethylene		-	-	-	-	-	-	-	-	-	-	-	-	+	-
Urea	10%	+	~	+	+	+	+	+	+	+	+	+	+	+	+
Urine		+	~	+	+	+	+	+	+	+	+	+	+	+	+
Vinegar		+	+	+	+	+	+	+	+	+	+	-	-	~	-
Vinyl acetate		-	-	-	-	+	~	+	+	+	+	-	-	+	-
Wine		+	+	+	-	+	+	+	+	+	+	+	+	+	-
Xylenes		-	-	-	-	-	-	~	-	-	-	-	-	+	-
Yeast		+	~			+	+	+	+	+	+	+	+	+	+
Zinc chloride		+	+	+	+	+	+	+	+	+	+	+	+	+	+

The data are provided as is and there is no warranty or representation, neither express nor implied, that they are free from errors. Van de Lande B.V. shall not be liable for any damages of any kind that may result from the use of this data. The information often is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance or reproducibility. Formulations presented may not have been tested for stability and should be used only as a suggested starting point. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user.